# Buddy3D

### **Product card**

#### PLA



exceptionally easy to print



ready to use on almost any type of FDM printer



high stifness



made with raw materials approved for food contact

# 1. GENERAL INFORMATION ABOUT THE PRODUCT

PLA (polilactyde) is one of the most popular and common material in 3D printing. It is odorless and biodegradable. It is recommended by most producers as a starting material it has low shrink age and it doesn't require special glue and bed heating, which makes it very easy to print.

#### Main PLA features:

- very easy to print
- ready to use in almost every FDM 3D Printer
- high sti f fness
- low temperature and chemical resistance

# 2. TECHNICAL PARAMETERS

CHARACTERISTICS	TEST METHOD	TEST CONDITIONS	IU	VALUE	
	ASTM				
PHYSICAL					
Density	D792	-	g/cm^3	1.24	
MECHANICAL	•				
Tensile strength	D882	-	MPa	60	
Breaking stress	D882	-	MPa	53	
Elongation at break	D882	_	%	6	
Modulus of flexibility	D882	-	GPa	3.6	
Bending strength	D790	-	MPa	83	
Modulus of elasticity	D790	_	GPa	3.8	
Notched impact strength, IZOD	D256	-	J/m	16	
THERMAL	•				
Deflection temperature under load	E2092	0.45 MPa	°C	55	

# 3. RECOMMENDATION OF PRINTING

PLA does not require drying before using. Satisfying results could be achieved by using standard settings for PLA in available slicers and printers. Cooling during printing is recommended.

#### Recommended parameters of printing:

Hotend temperature	200 - 230 °C
Bed temperature	50 - 60 °C
Print speed	< 300 mm/s

## 4. SAFETY NOTES

An exhaust fan is recommended.

Air filters in printers are recommended.

PLA needs to be used only in well-ventilated conditions.

Inhaling fumes generated during the printing must be avoided.

Generating fumes during printing depends mainly on printing temperature. In case of visibly rising emission levels, the printing needs to end. Check the hotend temperature and efficiency of the control system before using it next time.

In proper use conditions, the product doesn't endanger health.

#### It's forbidden to set fire or exceed decomposition temperature!

Decomposition of PLA is typically over 250 °C and it should be strictly avoided. The main ingredient of decomposition is lactide.

Detailed safety information is available in SDS.